

Green World Compounding  
 Parque Industrial de Alhama  
 C/ Alemania, s/n  
 30840 Alhama de Murcia  
 Murcia (España)  
 Tel: (+34) 968 63 22 21  
 Fax: (+34) 968 63 22 33  
 salvador.navarro@gwplastics-group.com  
 www.gwplastics-group.com

## Alfacom 30CRL Black

### Description

- Recycled fiberglass reinforced recycled polypropylene, chemically coupled
- 100% recycled compound
- Black color

### Properties

Physical properties	Method	Range
Melt Mass Flow Rate, MFR (230°C, 2,16kg)	ISO 1133	5 - 8 g/10 min
Fiberglass content	ISO 3451-1, A	27- 33 %
Mechanical properties	Method	Rango
Tensile stress at yield		40 – 60 MPa
Tensile modulus	ISO 527-1,-2	4.500 – 5.500 MPa
Tensile strain at break		4 - 6 %
Flexural stress at yield	ISO 178	60 - 80 MPa
Flexural modulus		4.000 – 5.000 MPa

\* Average orientative values based on ISO norms and GWC test method; not to be construed as specifications.

Rev. Std  
 Date 14-03-20  
 SNN

